

Technical Data Sheet

Absonet Superior Plus

COMPOSITION: Calcined attapulgite.

TECHNICAL INFORMATION

PHYSICO-CHEMICAL PROPERTIES

	Specifications ¹
Moisture (%)	Max. 5.0
Bulk density (g/l)	560 – 620
Water absorption ² (%)	Min. 110
Gasoil absorption ² (%)	Min. 100
Particle size distribution by Dry Sieving (%)	
Residue on 3.35 mm	Max. 2.0
Finer than 0.60 mm	Max. 10.0
	Typical value ³
Fuel oil absorption ³ (%)	57.0
Water absorption ³ (%)	125
Gasoil absorption ³ (%)	110

(1) Applicable to the whole batch. Uncertainty of the method is not included

(2) According to standard NF T 90-361.

(3) Typical value. It does not represent a specification.

