Datasheet floorpads

	White	Tan	Red	Blue	Green	Brown	Black
Weigth/Oz. Per sq yd (b)	21	30	32	29	40	45	55
Thickness-mm(c)	23 - 25	23 - 25	23 - 25	23 - 25	23 - 25	23 - 25	23 - 25
Thickness-inches(d)							
Fiber Type	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester
Binder Sytem	(e)	(e)	(e)	(e)	(e)	(e)	(e)
Binder Application	Spray	Spray	Spray/Dip	Spray/Dip	Spray/Dip	Spray/Dip	Spray/Dip
Abrasive Application	n/a	n/a	n/a	Dipped	Spray/Dip	Spray/Dip	Spray/Dip
Abrasive Type	n/a	n/a	n/a	n/a	n/a	n/a	n/a
Color	White	Tan to Brown	Bright Red	Blue	Green	Dark Brown	Black
Primary Usage	Buffing/Polishing	Buffing/Cleaning	Buffing/Polishing	Cleaning/Scrub	Strip/Scrub	Stripping	Stripping
Recommended RPM(f)	350 - 800	350 - 800	350 - 800	150 - 350	150 - 350	150 - 350	150 - 350

	Nat. Hair	Nat Grey	Light Blue	Ivory	Agressor		
Weigth/Oz. Per sq yd (b)	31	31	29	30	55		
Thickness-mm(c)	26	26	26	26	22		
Thickness-inches(d)							
Fiber Type	Poly/Natural	Poly/Natural	Polyester	Polyester	Polyester		
Binder Sytem	(e)	(e)	(e)	(e)	(e)		
Binder Application	Spray/Dip	Spray/Dip	n/a	Spray/Dip	Spray/Dip		
Abrasive Application	n/a	n/a	n/a	n/a	Dipped		
Abrasive Type	n/a	n/a	n/a	n/a	n/a		
Color	Beige/Hair Mix	Grey/Black	Pale/Baby Blue	Light Beige	Dark Purple		
Primary Usage	Burnishing	Burnishing	Burnishing	Burnishing	Cleaning/Scrub		
Recommended RPM(f)	1000+	1000+	1000+	1000+	1000+		

Datasheet floorpads

Details

(a)	Various sizes are available
(b)	+ or - 10%
(c)	= or - 10%
(d)	+ or - 1/8 inch
(e)	Cross Links
(f)	Recommendation only - These pads may be used at various machine speeds.
n/a	not applicable

General Construction:

These pads are a nonwoven product webbed from polyester or nylon/polyester fiber blends.
An abrasive material may be added to increase the overall agressiveness of the product.
They are sprayed and/or dipped with a cross-linking water-based binder system for strenght.
Polyvinyl chlorides are not used.

Im the manufacturing process.: Grit size based on ASTM E-11.

All details are specific E-Line floorpad features.